

## Consumable inspection visual aid



©4/2023 Hypertherm, Inc. Revision 4 897670EN-EU



# Overused







### Consumable inspection visual aid

#### Underused

A new electrode wears rapidly for the first 10% of life.

Copper body should remain clean and shiny even at end of life; signs of gravish heat discoloration could indicate a cooling issue within the torch.

#### Still usable

Even with little use, it is normal for an electrode to show marks and discoloration.

Make sure the o-ring(s) feel flexible and lubricated at all times. Heat can affect o-rings after use.

The hafnium insert should not lose its circular shape and should be fully centered.

than 2 mm.

### **Fully used**

The hafnium is eroded, but copper is intact. Color is dark. and/or white. Some cut quality is lost, with increased angularity on the cuts.

Time to replace your consumables.



SilverPlus: 1.25 mm pit-depth is approximately half life.



Copper: 0,5 mm to ~0,6 mm pitdepth is approximately half life.



Copper: Pit-depth should be less than  $\sim 0.9$  mm.

There should be no severe

discoloration of the silver.

SilverPlus: Pit-depth should be less



Top: The orifice should maintain its circular shape, with no dings or notches.

Cut quality is still optimal.

Make sure the o-rings feel flexible and lubricated at all times. Heat can affect them after use.



Orifices should be round with no nicks or heavy arc marks.

Any white material is hafnium oxide and can be easily cleaned out.



It is good practice to polish the front face of the shield with an abrasive pad to minimize spatter sticking to it.



SilverPlus: Pit-depth is 2.5 mm.

Copper: Pit-depth is 1,5 mm.



Top: The nozzle loses its round orifice, becoming oval or with notches.

Cut quality is lost as the shape and dimension of the orifice is damaged.



Internal: Too much debris and contamination inside the nozzle obstructs the flow of plasma.



Too much debris and contamination inside the shield will obstruct the flow of plasma.

For HPR<sup>®</sup> cartridge: Refer to shield images to assess wear.



Top: The orifice bore is perfectly round with sharp edges and no nicks.

Cut quality is still optimal.



Internal: Gas impurities, hafnium wear off, and some black or gray swirl marks are normal.

Orifices should be round with no nicks or heavy arc marks.

Any white material is hafnium oxide and can be easily cleaned out.



The internal and external orifices are round with sharp edges, and the bleed orifices are not plugged.

Use a light spray of water based anti spatter spray on front of the shield after installed; this can minimize spatter build-up.



©4/2023 Hypertherm, Inc. Revision 4 897670FN-FU



NOZZLE

SHIELD



#### Overused

This is close to a full blow-out and severe failure of all consumables and potentially the torch and system.

The material around the hafnium is eroded and a crater has formed at the tip of the electrode.

Misfires can occur when pit depth gets too deep as the heat transfer properties start to fail and electrode melts rapidly

Unacceptable cut quality and angularity on cut.



SilverPlus: Pit-depth is greater than 3 mm.



Copper: Pit-depth is greater than 2 mm.



Top: The copper is eroded around the orifice causing a loss of plasma constriction and damage to the shield.

This is close to a full blow-out and severe failure of all consumables and potentially the torch and system.



Internal: Excessive debris and contamination inside the nozzle obstructs the flow of plasma.



The shield loses its round orifice and sharp edges, becoming oval or with severe notches. This can cause nozzle orifice damage during pilot arc because the arc is not centered.

Replace shield if any deep scratches or gouges present. This may indicate the torch has crashed into the plate.